

Continuously Cast Iron

Unibar 300 (EN 16482 EN GJL-300C) (Guidance only)

Characteristics:

Unibar 300 is alloyed to achieve the specified properties, giving excellent wear resistance, strength & heat-treatment response compared to Unibar-200 and Unibar-250, while still possessing reasonable machinability and an excellent surface finish. Noise and vibration damping are excellent in this grade. Conforms to EN-16482:EN-GJL-300C.

Size Range:

UNIBAR STANDARD SIZES AND SUPPLY.	
Round	25mm – 700mm
Square	25mmx 25mm – 550mm x 550mm
Rectangle	Up to 650mm x 520mm
Supply condition	As-cast turned peeled milled cut.
Length	Standard 3080mm other lengths available

Chemistry:

ELEMENT	TYPICAL %
Carbon	2.95 - 3.45
Silicon	2.1 - 2.90
Manganese	0.55 - 0.75
Sulphur	0.04 – 0.07
Phosphorous	0.1 - 0.2
Others/Alloying	Residual
Iron	Balance


Typical Ranges: (Analysis at the discretion of UCB)

Mechanical Properties:

(Taken from mid-radius of cast bar, not separately cast test)

MATERIAL GRADE	MATERIAL SECTION	ANTICIPATED TENSILE VALUES N/mm ²	HARDNESS (BHN)	MATRIX
Unibar 300 EN 16482 EN GJL-300C	20 < D ≤ 50	220	190 - 260	Predominantly Pearlitic
	50 < D ≤ 100	205		
	100 < D ≤ 200	195		
	200 < D ≤ 400	185		

Grade
colour code



Density: 7.3 g/cc

Brinell Hardness (BHN): Test 10mm dia Ball 3000Kg load depending on section size. Hardness readings are taken across the entire section of the bar. Hardness values for rectangles depend on the ratio of height to width and can be supplied upon request.

Microstructure: Contains type 'A' graphite flakes in accordance with ISO 945. The rim zone contains fine types 'D' and 'E' interdendritic graphite. The core matrix is greater than 90% pearlite. The rim matrix is a ferrite/pearlite mixture. The rim may contain up to 5% dispersed fine carbides.

(Photo 100x magnification)



Heat Treat Response: Unibar 300 is suitable for all conventional methods of heat treatment, with hardness levels of up to Rc 50 achievable